

Tamaños de granallas

Tamaño nominal en mm	Malla	Granalla Esférica	Granalla Angular
2.00	10	S-780	G-10
1.70	12	S-660	G-12
1.40	14	S-550	G-14
1.18	16	S-460	G-16
1.00	18	S-390	G-18
0.85		S-330	
0.71	25	S-280	G-25
0.60		S-230	
0.42	40	S-170	G-40
0.30	50	S-110	G-50
0.18	80	S-70	G-80



Blasting S.A. Int. Amaro Avalos 3176 Munro (B1605EBX). Bs. As., Argentina

Tel. (54-11) 4762 2718 líneas rotativas. **Fax** (54-11) 4756 0217

email: info@blasting.com.ar / **web:** www.blasting.com.ar